

Grade: ASTM A182 Grade F6NM Stainless Steel (UNS S 41500, ASTM A182/A276 – chemistry only)

Type: Typically supplied in the solution annealed and double tempered condition (23 HRC maximum)

Nominal Composition	
Element	Weight %
Carbon	0.05 max
Silicon	0.6 max
Manganese	0.5 – 1.00
Phosphorus	0.30 max
Sulphur	0.30 max
Molybdenum	0.5 – 1.0
Chromium	11.5 – 14.0
Nickel	3.5 – 5.5

Mechanical Properties Condition

Solution annealed followed by quenching and double tempering

Property	Values
Ultimate Tensile Strength *	95 min Ksi (655 MPa)
0.2 % Yield Strength *	75 min Ksi (517 MPa)
Elongation *	17 % min
Reduction of Area *	35 % min
Charpy Impact Toughness	42 average / 34 min J at –60° C
Hardness	23 HRC

Notes

F6NM is a martensitic grade of stainless steel. The nickel and molybdenum content give the material high strength and excellent sub-zero impact properties.

The grade has improved weldability (may need post weld heat treatment for sour service) compared to other martensitic grades and has enhanced corrosion resistance. It has basic pitting and crevice corrosion resistance.

The material has good cracking resistance due to it's air hardening nature.

*Other non-NACE strength levels are available.

